



ALEXANDRIAN WHITE
TEST DATA

FOX
MARBLE

EN Standard

General Colouring	White with grey streaks
Country of Origin	Macedonia
Petrographic Examination	Marble
Application	Interior/Exterior
Finishes	Polished/Honed/Leathered/Bush Hammered
Abrasion Resistance (mm)	24.5
% Water Absorption at atmospheric pressure	0.18%
Apparent Density (kg/m3)	2830
Compressive Strength (MPa)	n/a
Open Porosity	n/a
Flexible strength under concentrated load (MPa)	0.5%
Slip Resistance	Polished Dry: 78, Wet:5 Honed Dry: 48, Wet: 11

ATSM Standard

Petrographic Examination	Marble (III)
Abrasion Resistance (Ha)	16.3
Water Absorption at atmospheric pressure	0.17%
Bulk Specific Gravity (kg/m3)	2833
Compressive Strength (MPa)	Dry: 167, Wet: 150

DISCLAIMER

These tests were carried out by a registered stone testing laboratory qualified and competent in performing such tests. The information contained is indicative only and cannot be relied upon as being information from Fox Marble.





www.foxmarble.net
info@foxmarble.net
+44 0207 380 0999