



ETRUSCO DORATO  
TEST DATA

**FOX**  
MARBLE

### EN Standard

General Colouring	Grey / Cream with pink and gold veining
Country of Origin	Kosovo
Petrographic Examination	Limestone - Intramicrite
Application	Interior/Exterior
Finishes	Polished/Honed/Leathered/Bush Hammered
Abrasion Resistance (mm)	20.5
% Water Absorption at atmospheric pressure	0.20%
Apparent Density (kg/m <sup>3</sup> )	2700
Compressive Strength (MPa)	Testing under way
Open Porosity	0.6%
Flexible strength under concentrated load (MPa)	12.3
Slip Resistance	Dry: 66, Wet: 64

### ATSM Standard

Petrographic Examination	Limestone
Abrasion Resistance (Ha)	17.1
Water Absorption at atmospheric pressure	0.1%
Bulk Specific Gravity (kg/m <sup>3</sup> )	2705
Compressive Strength (MPa)	Dry: 80, Wet: 68
Modulus of Rupture (MPa)	Dry: 8.6, Wet: 80

#### DISCLAIMER

These tests were carried out by a registered stone testing laboratory qualified and competent in performing such tests. The information contained is indicative only and cannot be relied upon as being information from Fox Marble.





[www.foxmarble.net](http://www.foxmarble.net)  
[info@foxmarble.net](mailto:info@foxmarble.net)  
+44 0207 380 0999