

GRIGIO ARGENTO TEST DATA FOX MARBLE



EN Standard

General Colouring	Plain grey with minimal white bioclasts
Country of Origin	Kosovo
Petrographic Examination	Limestone
Application	Interior/Exterior
Finishes	Polished/Honed/Leathered/Bush Ham- mered
Abrasion Resistance (mm)	19.5
% Water Absorption at atmospheric pressure	0.06
Apparent Density (kg/m3)	2700
Compressive Strength (MPa)	113
Open Porosity	0.20%
Flexible strength under concentrated load (MPa)	9.4
Slip Resistance	Dry: 56, Wet: 28

ATSM Standard

Petrographic Examination	Limestone
Abrasion Resistance (Ha)	23.3
Water Absorption at atmospheric pressure	0.09%
Bulk Specific Gravity (kg/m3)	2708
Compressive Strength (MPa)	Dry: 109, Wet: 96
Modulus of Rupture (MPa)	Dry: 8.9, Wet: 8.9

DISCLAIMER

These tests were carried out by a registered stone testing laboratory qualified and competent in performing such tests. The information contained is indicative only and cannot be relied upon as being information from Fox Marble.









www.foxmarble.net info@foxmarble.net +44 0207 380 0999