



ILLIRICO BIANCO  
TEST DATA

**FOX**  
MARBLE



### EN STANDARD

General Colouring	White
Country of Origin	Kosovo
Petrographic Examination	Limestone - Dolostone
Application	Interior/Exterior
Finishes	Polished/Honed/Leathered/Bush Hammered
Abrasion Resistance (mm)	20.5
% Water Absorption at atmospheric pressure	1.3%
Apparent Density (kg/m <sup>3</sup> )	2700
Compressive Strength (MPa)	Testing under way
Open Porosity	Testing under way
Flexible strength under concentrated load (MPa)	Testing under way
Slip Resistance	Testing under way

### ATSM Standard

Petrographic Examination	Marble (III)
Abrasion Resistance (Ha)	22.3
Water Absorption at atmospheric pressure	0.77%
Bulk Specific Gravity (kg/m <sup>3</sup> )	2562
Compressive Strength (MPa)	145
Modulus of Rupture (MPa)	9.3

#### DISCLAIMER

These tests were carried out by a registered stone testing laboratory qualified and competent in performing such tests. The information contained is indicative only and cannot be relied upon as being information from Fox Marble.







[www.foxmarble.net](http://www.foxmarble.net)  
[info@foxmarble.net](mailto:info@foxmarble.net)  
+44 0207 380 0999