



ILLIRICO SELENE
TEST DATA

FOX
MARBLE

FOX MARBLE

Illirico Selene

EN Standard

General Colouring	Grey
Country of Origin	Kosovo
Petrographic Examination	Limestone - Dolostone
Application	Interior/Exterior
Finishes	Polished/Honed/Leathered/Bush Hammered
Abrasion Resistance (mm)	19.5
% Water Absorption at atmospheric pressure	0.28
Apparent Density (kg/m3)	2690
Compressive Strength (MPa)	Dry: 38, Wet: 11
Open Porosity	1.1%
Flexible strength under concentrated load (MPa)	15.3
Slip Resistance	Dry: 38, Wet: 11

ATSM Standard

Petrographic Examination	Marble (III)
Abrasion Resistance (Ha)	23.3
Water Absorption at atmospheric pressure	0.77%
Bulk Specific Gravity (kg/m3)	2562
Compressive Strength (MPa)	145
Modulus of Rupture (MPa)	9.3

DISCLAIMER

These tests were carried out by a registered stone testing laboratory qualified and competent in performing such tests. The information contained is indicative only and cannot be relied upon as being information from Fox Marble.





www.foxmarble.net
info@foxmarble.net
+44 0207 380 0999